

# RECENT ADVANCES IN ECO-FRIENDLY SYNTHESIS AND CHARACTERIZATION OF ZINC OXIDE NANOPARTICLES FROM ECOLOGICAL SOURCES FOR BIOMEDICAL AND PHOTOVOLTAIC APPLICATIONS

*E.S. ADEWI\**, *K. SESIME\**, *A.D. HOUNSI\**, *K.J.B. AMEWOTEPE\**, *K.A. DONKATA\**,  
*M.M. DZAGLI\*<sup>##</sup>*, *M.A. MOHOU\**

<https://www.doi.org/10.59277/RJB.2024.4.01>

\*Laboratoire LPMCS, Département de Physique, Faculté des Sciences, University of Lomé,  
01BP1515 Lomé, Togo

\*\*Regional Centre of Excellence on Electricity Management (CERME), University of Lomé, Togo,  
#e-mail: mdzagli@gmail.com

*Abstract.* Studies have demonstrated the remarkable properties of nanoparticles and their many applications due to their size. While conventional synthesis of nanoparticles including physical and chemical methods has proven to be very expensive and sources of environmental pollution and potential health problems, harmless and eco-friendly nanoparticles were obtained by the green approach from biological materials and were used in many sectors of activities. Zinc oxide nanoparticles (ZnONPs) have been recently the subject of intense studies due to their innumerable advantages, among which the most remarkable are their wide band gap, high excitonic binding energy, biocompatibility, and stability. ZnONPs were used for the antimicrobial, antifungal, anti-diabetic, anti-inflammatory, and antioxidant activities, the improvement of agriculture and food industry, and that of photovoltaic devices and storage. This review focuses on the green synthesis of ZnONPs from different biological materials, their characterization, and their potential applications. This review provides a better understanding of the biosynthesis, characterization techniques, and applications of ZnONPs in various sectors of activity.

*Key words:* ZnO nanoparticles, green synthesis, biological extracts, characterization techniques, biomedical and photovoltaic applications.

## INTRODUCTION

Nanoscience and nanotechnology deal with the study and production of nanoscale materials whose size or one of their dimensions is smaller than one hundred nanometers [17, 27, 56, 72, 133]. The nanoscale offers a high surface-to-volume ratio and more reactivity, which endows nanoparticles with functions that are not observed in their bulk materials [65, 70, 86].

---

Received: June 2024;  
in final form September 2024.

Nanoparticles have various biological, chemical, and physical properties such as catalytic, electrical conductivity, nonlinear optics, mechanical strength, heat capacity, wound healing anti-inflammatory, and antimicrobial properties [74, 120, 127].

Nanotechnology is also used in industry, computing, energy generation and storage, agriculture, optics, drug delivery, and environmental science [49, 86]. The major methods of nanoparticle synthesis are physical, chemical, and biological processes that confer specific shape and size that are essential for their applications in different fields [19, 76, 92, 166]. The green synthesis method is emerging today as the most popular choice to produce nanoparticles to the detriment of traditional approaches (physical and chemical) due to the environmental aspects and potential applications [64, 87]. The green synthesis is a fast, practical, and eco-friendly process that uses biological materials including plants extracts, fungi, bacteria and algae [7, 49, 93, 130, 150, 155].

Zinc oxide (ZnO) is an inorganic material that has a multitude of physical and chemical properties including high chemical stability, high electrochemical coupling coefficient, a wide range of radiation absorption, and high photostability [24, 113]. The various crystal structures of ZnO are hexagonal wurtzite, zinc blende, and rock salt. In addition, ZnO is a semiconductor of the group II–VI that has a band gap of 3.37 eV. It is safe and easily available with good transparency. It possesses a large excitation binding energy of 60 MeV, a high mobility of electrons, negligible cytotoxicity, with strong luminescence at room temperature, and high piezoelectric and pyroelectric properties, which has attracted much interest recently [140, 158]. All these properties enabled various applications of ZnO in multiple fields such as surface acoustics, wave devices, gas detection and optoelectronics, coupled sensors, chemical sensors, electronics of spin, personal care products, coatings and paints [127, 157, 158]. ZnO has been used successfully in some devices including semiconductor lasers, optically transparent electrodes, ultraviolet photodetectors, transparent thin-film transistors and LEDs, solar cells, gas sensors, ceramics, catalysts, and cosmetics [88, 157].

The development of new materials is a necessity, therefore particular attention is paid to the use of nanomaterials because their properties can be modulated by controlling their size and shape [28]. ZnO nanoparticles (ZnONPs) have exhibited enhanced physicochemical properties compared to the bulk form of ZnO [123]. ZnONPs have received much consideration with promising applications in various industrial fields such as solar cells and energy storage, UV light emitting devices, gas sensors, photocatalysts, as well as pharmaceutical, biomedical, cosmetic, and agricultural products [49, 70, 115, 120, 126, 133, 134]. The excellent antimicrobial properties of ZnONPs have facilitated their uses in antiseptic creams, shampoos and calamine lotions for surgical tapes [7], in removing sulfur and arsenic from water [86], and in disinfection of water and wastewater [40].

The current market demand concerns the manufacture of novel nanomaterials for refining petrochemicals, healthcare, microelectronics, cosmetics, and energy

production. Therefore, nanoparticle synthesis methods from ecological, non-toxic, and advantageous sources are of paramount importance to prevent environmental and health problems [8]. This review covers the synthesis methods of ZnONPs using different ecological sources, as well as their characterization techniques. Various sectors of applications are also discussed.

### THE SYNTHESIS OF NANOMATERIALS

Since the discovery of nanomaterials, several methods have been investigated to optimize their synthesis process. The synthesis methods of nanoparticles are based on two main approaches: the bottom-up approach and the top-down approach [48, 81, 149]. Synthetic techniques are summarized in Fig. 1.




Fig. 1. Different synthesis methods of nanoparticles.

#### TOP-DOWN APPROACH

The top-down approach consists of disintegrating the bulk material into the required nanostructure. This approach generally relies on physical methods including laser ablation, evaporation-condensation, ball milling, pulsed wire discharge, vapor and gas phases and lithography. Most of them are used in the synthesis of ZnONPs [7, 86, 104]. Previous studies have revealed that the laser ablation method offers unique advantages as it allows the production of a narrow

size and shape distribution, and high purity [94]. The efficiency and morphological features depend on the ablation time and the wavelength of the laser [85]. Unfortunately, physical synthesis methods are expensive and time-consuming, have high energy consumption, and require a large space for equipments [49, 157, 163].

#### BOTTOM-UP APPROACH

In the bottom-up approach, nanoparticle synthesis is based on the self-assembly of atoms into a particle at the nanometric scale. The bottom-up approach uses chemical and biological methods [98]. The synthesis of nanoparticles can utilize chemical methods comprising chemical reduction, sonochemistry, photochemistry, electrochemistry, pyrolysis, sol-gel transformations, microwave oven processing, solvothermal processes, and coprecipitation [86, 104].

The sol-gel method is the most widely used among these methods because of its simplicity, robustness, repeatability, and relatively mild conditions [113]. ZnONPs synthesis process uses a chemical reagent and a zinc precursor salt to regulate the pH of the solution and prevent the precipitation of  $\text{Zn(OH)}_2$ . Subsequently, the solution is heat-treated at high temperatures to obtain ZnONPs [30]. Chemical stabilizers, such as citrates or polyvinylpyrrolidone, are generally added during the synthesis process to control morphological properties and prevent agglomeration of ZnONPs [158]. It has been reported that the concentration of zinc precursor and other reagents used during the synthesis process significantly affect the shape and the size of ZnONPs, which could range from nanometers to micrometers [98].

Chemical methods have the disadvantage of involving toxic products, high temperatures and pressures, and expensive equipment and reagents [100]; therefore, they can lead to environmental contamination. Chemical methods have proven to produce nanoparticles containing debris of toxic compounds on their surface, which would limit their medical applications [130]. Therefore, biological or green synthesis methods of nanoparticles are considered better choices than physical or chemical methods [10, 25, 159].

#### THE GREEN SYNTHESIS OF ZINC OXIDE NANOPARTICLES

Green synthesis is a reliable, reproducible, low-cost and environmentally friendly method [21]. Green synthesis uses plants, bacteria, fungi, microbial cell-based systems, yeasts, enzymes, biomolecules, and microorganisms. The process is usually carried out at mild pH, low pressure, room temperature, avoiding hazardous materials and conditions; moreover, it is also cost effective [86]. Green synthesis

from plants is becoming one of the most preferred and explored methods [97], because it is clean, cost-effective, fast, often uses one-step protocols, allows for controlled synthesis with well-defined size and shape. The nanoparticles prepared by green synthesis are non-toxic, and can be used in many different sectors, including medicine [99, 158].

#### FROM MICROBES

Bacteria are also used for the green synthesis of nanoparticles, but this approach has drawbacks such as the high cost related to the media for the production of bacteria, and the long time for screening microbes to prevent possible contamination [4]. Nevertheless, several microbial strains have been studied and are involved in the synthesis of ZnONPs. For example, the probiotic bacterium *Lactobacillus plantarum* VITES07 was used as an ecological reducing and styling agent to synthesize stable ZnONPs in hexagonal phase, with a roughly spherical shape and an average particle size between 7 and 19 nm [137]. A metabolically versatile actinobacteria *Rhodococcus pyridinivorans* NT2 was used also to synthesize a stable, hexagonal phase, roughly spherical ZnONPs, with an average particle size between 100 and 120 nm to improve anti-UV, self-cleaning and antibacterial properties [77]. The ureolytic bacterial species *Serratia ureilytica* (HM475278) were used to synthesize ZnONPs on cotton fabric and the particle size ranged from 7 to 19 nm and the shape was a spherical nanoflower [38]. The biosynthesized ZnONPs from reproducible bacteria, *Aeromonas hydrophila* as an environmentally friendly reducing and styling agent were investigated and an absorbance peak of 374 nm was obtained. The resulting nanoparticles had a spherical and oval shape with an average size of 57.72 nm. The antimicrobial activities of the ZnONPs against *Pseudomonas aeruginosa* and *Aspergillus flavus* showed a zone of maximum inhibition [66]. The synthesis of ZnONPs mediated by *Lactobacillus sporogens*, a probiotic microbe, was improved successfully and the resulting particles had a hexagonal structure with a size-range from 5 to 15 nm [107]. Table 1 lists important results from the use of microbes in the synthesis of ZnONPs.

Table 1

Examples of ZnONPs made using bacteria

Microbial strain	Family	Size (nm)	Shape / Structure	Activity performed
<i>Plantarum</i> SPEED07 [137]	<i>Lactobacillaceae</i>	7–19	hexagonal	
<i>Rhodococcus pyridinivorans</i> NT2 [77]	–	100–120	hexagonal	anti-UV, self-cleaning and antibacterial

<i>Serratia ureilytica</i> [38]	<i>Yersiniaceae</i>	7–19	spherical to nanoflower	antibacterial
<i>Aeromonas hydrophilia</i> [66]	<i>Pseudomonadaceae</i>	57–72	spherical, oval	antibacterial
<i>Lactobacillus sporogens</i> [107]	<i>Bacillaceae</i>	5–15	hexagonal unit cell	adsorption study
<i>Nostoc</i> [91]		28.21	spherical	antimicrobial assays
<i>Streptomyces sp</i> [142]	<i>Streptomycetaceae</i>	15–30	spherical	antibacterial, antioxidant activities
<i>Acinetobacter schindleri</i> SIZ77 [31]	–	20–100	spherical	antibacterial activity

#### FROM FUNGI

Fungi excrete important extracellular reducing enzymes, making them good candidates for nanoparticle synthesis [69]. Their proven tolerance to metal ions and their bioaccumulation capacities are linked to their capacity to produce nanoparticles [86]. ZnONPs have been synthesized using several fungal strains [129]. Thus, *Candida albicans* was successfully used to synthesize ZnONPs and revealed a size varying from 15 to 25 nm [140]. The *Aspergillus fumigatus* was employed in the synthesis of ZnONPs and confirmatory tests showed a nanoparticle with an average size of 3.8 nm [119]. Table 2 shows some fungi used for the synthesis of ZnONPs.

Table 2

Examples of ZnONPs using fungi

Fungal strain	<i>Candida albicans</i> [140]	<i>Aspergillus fumigatus</i> [119]
Family	<i>Saccharomycetaceae</i>	<i>Trichocomaceae</i>
Size (nm)	15–25	1.2–6.8
Form	quasi-spherical, hexagonal phase (wurtzite structure)	oblate spherical and hexagonal shapes aggregated
Functional group	C=C, amide, open chain imino group	–
Activity carried out	catalytic performance in the synthesis of steroidal pyrazolines	effect on phosphorus mobilizing enzyme secretion and gum content of truss bean

#### FROM SEAWEED

Algae are photosynthetic aquatic chlorophyllous plants with no basic plant structure such as roots, leaves, flowers, and seeds [4]. Seaweed extracts are a rich source of many bioactive compounds characterized by a higher amount of

polysaccharides, compared to plant extracts [63]. Their functional compounds are metal ion-reducing and capping agents that could create a sustainable coating on nanoparticles in a single production step [17, 79]. The green synthesis of ZnONPs using seaweed extracts has gathered substantial interest due to their rapid growth, environmentally benign nature, and cost-effective protocols [55, 84]. Studies have shown that seaweed can be used in the synthesis of nanoparticles of silver, gold [138], metal oxides, and semiconductors [80]. Extracts of brown marine macroalgae *Sargassum muticum* were successfully used to synthesize ZnONPs which average size ranges from 30 to 57 nm in hexagonal wurtzite structure [25]. The synthesis of ZnONPs using *Ulva lactuca* was reported with particles of average crystallite size range from 10 to 50 nm, and maximum absorption at 325 nm [60]. Table 3 shows representative articles in which algae were used for the synthesis of ZnONPs.

Table 3

Examples of ZnONPs based on some algae

Seaweed strain (Family)	Size (nm)	Shape / Structure	Functional group	Activity carried out
<i>Sargassum muticum</i> (Sargassaceae) [25]	30–57	hexagonal wurtzite	asymmetric stretching band of the sulfate group, an asymmetric CO band associated with the CO-SO <sub>3</sub> and OH group, sulfated polysaccharides	
<i>Spirogyra hyalina</i> (Zygnemataceae) [55]	45	hexagonal wurtzite	alcohols, alkane, amide I–II, aromatic and aliphatic amines	antibacterial and antioxidant activities
<i>Ulva lactuca</i> (Ulvaceae) [60]	10-50	hexagonal wurtzite	sulfate group, hydroxyl groups, cyclic peptides	photocatalytic, antibiotic and insecticidal activities
<i>Sargassum myriocystum</i> (Sargassaceae) [95]	36	spherical, radial, triangular, hexagonal, rod	OH and C=O stretch band, carboxylic acid	
<i>Chlamydomonas reinhardtii</i> (Chlamydomonaceae) [124]	55–80	nanorod, nanoflower, porous nanosheet	C=O stretch, NH bending band of amide I and amide II, C=O stretch of zinc acetate, COC of polysaccharide	photocatalytic
<i>Gracilaria edulis</i> (Gracilariaceae) [109]	66–95	stem shape	alcohol, amide, nitro, vinyl groups	anti-cancer activity

## FROM PLANT EXTRACTS

Plant parts constitute the most used ecological source of nanoparticles; especially the roots, leaves, stems, seeds, fruits, and rhizomes are used for the synthesis of ZnONPs, thanks to their abilities to produce functional phytochemicals [4, 48, 56]. These phytochemicals are oxidants including flavonoids, polyphenols, amino acids, lipids, proteins and reducing sugars, carboxylic acids, amides, ketones, aldehydes, and alkaloids, which vary from plant to plant. They are used in the synthesis process as the reducing agents of ions into nanoparticles and stabilizers through capping processes [7, 77, 133]. For the plant extract: briefly, the plant part is thoroughly washed with distilled or deionized water, and could then be dried, ground into powder using a grinder, and dissolved in deionized water or alcohol. It is usually heated up to 60 °C for a few hours, or simply soaked, because prolonged exposure to high temperatures can lead to the decomposition of phytochemicals in the plant extract. The solution is then filtered using Whatman filter paper N° 1 to obtain the plant extract [32, 106, 161, 167]. Concerning ZnONPs synthesis, the extract could be used directly or could be dried to ensure the concentration of solid extracts. If the extract is in the form of an aqueous solution, it is then mixed with a solution of zinc salt; otherwise, the zinc salt and the solid extract of the plant are mixed in distilled water or alcohol. A sodium hydroxide solution is generally added to the mixture to bring the pH of the reaction medium back to 11, ideal for the synthesis of ZnONPs. The zinc salt acts as a precursor of ZnONPs, from which a precipitate is produced. The precipitate is then calcined to produce ZnONPs [62, 159, 172]. Figure 2 illustrates diverse procedures of ZnONPs synthesis from ecological sources. Phytochemicals were involved to contribute to the reduction and formation of nanoparticles, and to the stabilization as a capping agent by adhering to the surface of the nanoparticles as a protective layer and in controlling the size of particle [143, 163].




Fig. 2. Mechanism of the synthesis of ZnO nanoparticles from biological source.



Recent studies revealed that the concentration of plant extracts, the concentration of the precursors, the reaction time, the pH level, and the calcination temperature constitute the factors that determine the morphology and size of ZnONPs [27, 48, 172]. Table 4 shows the most remarkable achievements in ZnONPs synthesis from extracts of different plant parts.

Table 4

Different plants used for the synthesis of ZnONPs

Plants used for extraction	Part used	Size (nm)	Shape/structure	Functional groups	Activity performed
<i>Artemisia pallens</i> [54]	plant	50–100	hexagonal wurtzite	hydroxyl groups, aromatic ring, ketonic derivatives, atmospheric carbon dioxide impurity	antimicrobial activity
<i>Cinnamomum verum</i> [10]	leaf	18–25	spongy and flower		anti-cancer activity
<i>Plumbago auriculata</i> [87]	flower	35.34	hexagonal	gallic acid, chlorogenic acid and catechin	antiviral evaluation
<i>Camellia sinensis</i> [28]	leaf		hexagonal wurtzite	phenolic compounds, aromatic cycle, polyphenols	photocatalytic and biological applications
<i>Carica papaya</i> [51]	leaf	21	hexagonal wurtzite	alcohols, phenols, carboxylates, aromatic aldehydes	photocatalytic degradation
<i>Annona muricata</i> [136]	leaf	37	hexagonal of wurtzite	O–H, C–N, flavonoids, polyphenols and alkaloids	antibacterial activity
<i>Brassica oleracea</i> var. <i>botrytis</i> [83]	leaf	52	hexagonal wurtzite	hydroxyl, carbonyl, carboxylic and phenol groups	photocatalytic, antimicrobial and larvicidal activity
Grape seeds [58]	fruit	15.86			antibacterial and antioxidant activities
<i>Tabernaemontana divaricate</i> [114]	leaf	36.82	pure hexagonal wurtzite	steroids, terpenoids, flavonoids, phenylpropanoid, phenolic acids	photocatalytic and antimicrobial activity
<i>Cucumis melo</i> [22]	fruit	12.8	pure hexagonal	aliphatic amine, carboxylic acid, ether, alkynes	antibacterial activity
<i>Vigna mung</i> [62]	seed	26.47	spherical	OH groups, alkene group and amide II, ZnO	antibacterial, anticancer activity
<i>Aspalathus linearis</i> [39]	plant		quasi-spherical	phenolic compounds	
<i>Pelargonium odoratissimum</i> [1]	leaf	34.12	pure hexagonal Wurtzite	–OH, –CH, O=C=O, C=C, CN, CO, –CH, Zn–O	antioxidant, antibacterial and anti-inflammatory activities

<i>Portulaca oleracea</i> [75]	plant	16–58	hexagonal wurtzite	carboxylic acid, alcohol groups, phenolic components and flavonoids	photocatalytic activities
<i>Solanum torvum</i> [47]	leaf	28	spherical		evaluation of the toxicological profile
<i>Syzygium cumini</i> [112]	leaf	16.41	hexagonal and spherical	flavonoids, phenolic acids, enzymes and steroids	seed germination and purification and waste water
<i>Nyctanthes arbor-tristis</i> [122]	leaf	21.45	hexagonal wurtzite	protein, –OH	antioxidant and antimicrobial activity
<i>Becium grandforum</i> [67]	leaf	20	pure wurtzite	phenols, flavonoids, saponins, glycosides, steroids, tannins and alkaloids	antimicrobial activity and adsorption of methylene blue
<i>Cayratia pedata</i> [65]	leaf	52.24	hexagonal	Zn – O, OH, CN, CO, C=C, =CH	immobilization of the enzyme Glucose oxidase
<i>Cassia fistula</i> [155]	leaf	5–15	hexagonal of wurtzite	polyphenols and flavonoids	photodegradative, antioxidant and antibacterial activities
<i>Scadoxus multiflora</i> [14]	leaf	31 ± 2	spherical	–C=O and C–H	antifungal, ovicidal and larvicidal properties
<i>Limonium pruinatum</i> [96]	plant	41	hexagonal / cubic	alcohols, phenols, terpenoids and esters	evaluation of anti-skin cancer, antimicrobial and antioxidant potentials
<i>Sambucus ebulus</i> [12]	leaf	17	würtzite	OH, NH, CO, RCOO,	antibacterial activity and photocatalytic degradation
<i>Tilia tomentosa</i> [144]	leaf	80	single-phase hexagonal	–	dye-based solar cells
<i>Glycosmis pentaphylla</i> [164]	leaf	32–36	hexagonal of wurtzite	–OH, alkane -CH, CH, C=O	antimicrobial activity
<i>Atalantia monophylla</i> [166]	leaf	33.01	hexagonal	hydroxy group, alkane group, aromatic amine, acids, terpenoids and aromatic dicarboxylic acids, amides,	bacterial and fungal destruction
<i>Swertia chirayita</i> [6]	plant	2–10	spherical	Polyols	antibacterial activity
<i>Hedera nepalensis</i> [102]	leaf				antibacterial activity

<i>Garcinia mangostana</i> [20]	fruit	21	spherical	phenols, flavonoids, xanthones, anthocyanins, with the functional groups OH, C=O, COOH, C–O–C	photocatalytic activity
<i>Andrographis paniculate</i> [115]	leaf	13.8	spherical and hexagonal	phenolic compounds, terpenoids and proteins	antioxidant, antidiabetic and anti-inflammatory activities
<i>Alstonia macrophylla</i> [9]	leaf		hexagonal of wurtzite	–	<i>in vitro</i> anti-cancer activity
<i>Mangifera indica</i> [117]	leaf	45–60	spherical and hexagonal	–	antioxidant activity and cytotoxic effects
<i>Lantana aculeate</i> [97]	leaf	12±3	spherical	–	antifungal activity against fungal plant pathogens
<i>Passiflora foetida</i> [73]	fruit	58	hexagonal wurtzite	phenol, amide, flavonoid, carboxylate group	photocatalytic activity
<i>Phoenix dactylifera I</i> [28]	leaf	19.77–26.28	hexagonal wurtzite	O–H group; saturated hydrocarbons; the carbonyl group, aromatic ring and C–OH bonds.	–
<i>Hybanthus enneaspermus</i> [145]	leaf stem, root				–
<i>Sesbania grandiflora</i> [116]	leaf	15–35	spherical	OH stretch bond, Zn–O stretch.	–
<i>Aloe vera</i> [170]	leaf	25	sphere-like and hexagonal	–	antimicrobial and antioxidant activities
<i>Corriandrum sativa</i> [53]	leaf	66, 81	hexagonal wurtzite	alcohol, aldehyde and amine	–
<i>Eichhornia crassipes</i> [158]	leaf	32 ± 4	spherical	–	–
<i>Salvia officinalis</i> [2]	leaf	26.14±2.46		amino acids, flavonoids, vitamins, polyphenols	photocatalytic and antifungal activities
<i>Trema orientalis</i> (L) [110]	leaf	24	crystalline		photocatalytic degradation of zoxamide
<i>Ixora coccinea</i> [171]	leaf	145.1	spherical	zinc oxide bond	
<i>Physalis alkekengi</i> L. [111]	shoots	72.5	hexagonal		
<i>Parthenium hysterophorus</i> L. [118]	leaf	27±5 and 84±2	spherical and hexagonal		size-dependent antifungal activity against fungal plant pathogens

<i>Passiflora caerulea</i> [131]	leaf	37.67	spherical shape	amines and alkanes	antibacterial effect was visualized against pathogens of urinary tract infections.
<i>Limonia acidissima</i> L. [103]	leaf	12–53	spherical	phenol, carboxylate group, guaiacyl ring carbonyl, aromatic ring	mycobacterium growth tuberculosis
<i>Trifolium pratense</i> [42]	flower	60–70	crystalline		antibacterial activity
<i>Plectranthus amboinicus</i> [165]	leaf	20–50	agglomerated, spherical and hexagonal	secondary amines, alcohols, alkanes, phenolic, carbonyl and carboxylic compounds	
<i>Hibiscus subdariffa</i> [26]	leaf			alcoholic, secondary amine and aromatic ring	effect of temperature on synthesis, anti-bacterial activity and anti-diabetic activity
<i>Azadirachta indica</i> (L.) [44]	leaf	18	spherical	polyols, aromatic rings, amines, carboxylic acid	
<i>Pongamia pinnata</i> [152]	leaf	100	spherical	free carbonyl group, carboxylic groups, esters	antibacterial activity of ZnO nanoparticles and treated cotton
<i>Calotropis gigantea</i> [162]	leaf	30–35	spherical		
<i>Anisochilus carnosus</i> [21]	leaf	56.14, 49.55, 38.59	hexagonal and spherical wurtzite		photocatalytic degradation of methylene blue.
<i>Courupita guianensis</i> aubl [133]	leaf		hexagonal	Polyphenols, aromatic compounds, phenolic compounds	bactericidal effect against human pathogens.
<i>Solanum nigrum</i> [120]	leaf	29.79	hexagonal wurtzite and spherical		
<i>Spathodea campanulata</i> [100]	leaf	20–50	spherical	polyphenols, polyphenols and proteins	
<i>Laurus nobilis</i> [163]	leaf	24	hexagonal wurtzite		antibacterial assay, anticancer activity, antibiofilm assay
<i>Ocimum tenuiflorum</i> [127]	leaf	13.86	hexagonal	alcohol, carboxylic acid, ether	

<i>Myristica fragrans</i> [49]	fruit	41.23	spherical	hydroxyl groups (OH), carbohydrate rings (C-O), (CC)	evaluation of antibacterial, antidiabetic, antioxidant, antiparasitic and larvicidal properties.
<i>Agathosma betulina</i> [157]	leaf	15.8	hexagonal wurtzite	hydroxyl group, Zn-O	varistor response
<i>Artemisia annua</i> [139]	leaf	21.34–24.71	hexagonal wurtzite		
<i>Calotropis proceed</i> [52]	leaf	15–25	spherical	hydroxyl, aldehyde, amine, ketone and carboxylic acid groups	photocatalytic application for the degradation of methyl orange under UV light

### THE CHARACTERIZATION TECHNIQUES OF ZnO NANOPARTICLES

The physical and chemical characteristics of nanoparticles are of interest both from the fundamental and applicative points of view. The optical, mechanical, magnetic, and electrical properties are essential characteristics of ZnONPs for their potential applications including electronics and energetics. Biomedical and environmental applications, on the other hand, mainly rely on their chemical properties, including reactivity, stability, sensitivity, and toxicity [74].

ZnONPs are investigated using numerous complementary analytical techniques reported in the literature [16]. The optical energy band gap of crystalline and amorphous materials was obtained using ultraviolet-visible (UV-Vis) spectroscopy [35, 36]. X-ray diffraction (XRD) analysis was used to determine the crystal structure, the phase and the average size of ZnONPs from the diffraction peaks [34, 74]. Energy dispersive X-ray analysis (EDX) was used to determine the purity and the elemental composition of ZnONPs [23]. The details about the surface morphology and topography were investigated using atomic force microscopy (AFM) imaging [141]. Isolated and aggregated particles could be identified using transmission electron microscopy (TEM) imaging [71]. Fourier transform infrared spectroscopy (FTIR) revealed the functional behavior of ZnONPs. Scanning electron microscopy (SEM) imaging confirmed the shape, structure, and size of the nanoparticles. FTIR used in attenuated total reflectance (ATR) mode can be used as nondestructive technique for identifying metabolites, and other chemicals. Figure 3 presents a summary of ZnONPs characterization techniques.

Raman spectroscopy helps to characterize the quality of the crystal structure, oxygen vacancies, and zinc excess, or surface impurities. X-ray photoelectron spectroscopy (XPS) analysis can be used for morphology, bioactive surface, and surface chemistry characterization [82]. Dynamic light scattering (DLS) analysis is

considered as a non-destructive approach to characterize compounds in suspensions and solutions. Photoluminescence analysis (PL) was used to determine the band gap, crystalline purity, and to spot impurities. Thermal gravimetric-differential thermal analysis (TG-DTA) was used to characterize the thermal stability, phase transition, and effect of the oxidative and reductive environment of the nanoparticles [4, 68, 156].




Fig. 3. Main characterization techniques of ZnONPs.

### APPLICATIONS OF ZnONPs

ZnONPs have many fields of application; this section discusses part of them, with main focus on biology and energy production.

#### APPLICATIONS IN AGRICULTURE

The use of pesticides in agriculture and the use of antibiotics for the treatment of farm animals has led to the increase of multi-resistant bacterial and fungal strains [3, 90]. Therefore, metal nanoparticles have received considerable attention in agriculture recently [50, 91, 119, 126]. In particular, ZnONPs were used in the treatment of fungal and other microbial infections in farm animals and plants, being considered an effective alternative to conventional antibiotics. ZnONPs have been reported to demonstrate excellent pesticidal efficacy against *Artemia salina* larvae [172]. The pesticidal effects were investigated on soils infested with the *Fusarium* and the *Verticillium wilt* fungi, respectively by spraying ZnONPs on tomato and eggplant to increase their yields [43]. The small size and appropriate chemical

composition of ZnONPs enhance their interaction with the bacterial wall and favor their penetration in bacteria to damage and kill them.

Furthermore, the use of ZnONPs as nanofertilizer could increase the yield and growth of food crops. ZnONPs were used to promote seed germination, seedling vigor, and plant growth [132]. The increase of stem and root growth of peanuts by the use of ZnONPs was demonstrated effectively in literature [108]. ZnONPs colloidal solution can substitute organic fertilizers to enhance the development of plants. The use of these nanoparticles as biological fertilizers could reduce chemical residues in vegetables, could revive soils, and could increase the growth and yield of crops [89, 171]. Nanofertilizers offer the advantage of being used in very small quantities [11]. Nanopowders of metallic nanoparticles can also be successfully used as fertilizers and pesticides to obtain an increase in yield of plants such as wheat plants [29].

#### ANTIMICROBIAL AND ANTIBACTERIAL USES

Infectious diseases caused by parasites, protozoa, bacteria, viruses and fungi constitute a major concern for researchers around the world [125]. The development of antibiotics, antimicrobials, antifungals, and antivirals aims to fight infectious diseases [6, 121]. However, the administration of high doses of antibiotics generates high toxicity and increases resistance to drugs [122, 136]. Therefore, several nanomaterials are used as antimicrobial and antiviral agents for various applications such as drug delivery, biosensing, and tumor cell elimination, demonstrating high efficiency compared to conventional techniques [5, 101, 148]. Stan *et al.* investigated anti-bacterial activity of biosynthesized ZnONPs using extracts of *Allium sativum*, *Rosmarinus officinalis* and *Ocimum basilicum* against *Staphylococcus aureus*, *Bacillus subtilis*, *Listeria monocytogenes*, *Escherichia coli*, *Salmonella typhimurium*, and *Pseudomonas aeruginosa* bacterial strains and their results demonstrated that the antibacterial and antioxidant activities of the green synthesized nanoparticles were enhanced compared to their chemically synthesized counterparts [151]. The combination of antibiotics and ZnONPs using *Aloe vera* extract demonstrated an effective clinical elimination of isolates of methicillin resistant *Staphylococcus aureus* [15]. The biosynthesized ZnONPs using the extract of *Dysphania ambrosioides* demonstrated similar inhibitory effect on *S. aureus* and *S. epidermidis* compared to the use of chlorhexidine [18]. The inhibitory effect on the growth of *B. subtilis* and *P. aeruginosa* was carried out using ZnONPs synthesized from *Lawsonia inermis* leaf extract [172]. The use of *Trifolium pratense* flower extract based ZnONPs on strains of *S. aureus* and *P. aeruginosa* and standard strain of *E. coli* has shown an effective inhibitory effect [42]. The antibacterial activity of ZnONPs synthesized using the *Artemisia* plant pallens was carried out against gram-positive *B. subtilis*, *S. aureus* and gram-negative *E. coli* and it demonstrated an inhibitory effect [62]. Excellent antioxidant and bactericidal activities were obtained

using biosynthesized ZnONPs from *Cassia fistula* plant extract on *Klebsiella aerogenes*, *E. coli*, *Plasmodium desmolyticum* and *S. aureus* [155]. ZnONPs biosynthesized using *Sambucus ebulus* antibacterial activity was carried out against *B. cereus*, *S. aureus* and *E. coli* bacteria [12]. Excellent bactericidal activity was demonstrated using *Ulva lactuca* based ZnONPs against gram-positive (*Bacillus licheniformis* and *Bacillus pumilis*) and gram-negative (*E. coli* and *Proteus vulgaris*) bacteria [60]. The effective inhibitory effect of ZnONPs obtained using grape seed extract was demonstrated on the growth of *S. aureus* [58].

#### PHOTOCATALYTIC ACTIVITY

Water quality is a global challenge nowadays and the increase of environmental pollution is caused by water contamination [78]. The treatment of water and wastewater by the approach of photocatalytic degradation of the organic pollutants is a promising approach to the detriment of current methods of inactivation, such as adsorption on activated carbon, filtration, chemical treatment, sedimentation, and biological treatment as they fail to achieve extensive removal of pollutants to fully purify the water [62, 73, 83, 112].

ZnONPs have been frequently used for the degradation of many organic pollutants due to their larger surface area, smaller particle size, and UV radiation absorption [83, 155, 172]. The photocatalytic activities of ZnONPs biosynthesized using biological source extracts such as the *Prunus fruit*, the *Cassia fistula* plant, *Sambucus ebulus*, and *Camellia sinensis* leaf, were carried out successfully under UV and solar lighting for the degradation of a methylene blue solution [2, 12, 134, 148, 155]. ZnONPs are considered one of the best photocatalysts to disinfect wastewater, break down pesticides and herbicides, and corrupt methylene blue dye [60, 124, 145].

#### ANTIOXIDANT ACTIVITY

The high antioxidant properties of ZnONPs can be explained by the presence of phenolic species in plant extracts, which is an important characteristic for bio-applications. ZnONPs synthesized using biological extracts showed interesting antioxidant activities [58, 122, 160]. The comparison between the antioxidant activities of ZnONPs obtained from extracts of *Allium sativum*, *Rosmarinus officinalis* and *Ocimum basilicum* was carried out and a strong effect was observed [12].

#### ANTILARVICIDAL APPLICATION

Various studies reported the antifungal and antilarvicidal activities of ZnONPs biosynthesized for the treatment of yeasts, fungi, and harmful insects which are



major ailments in agriculture and mosquito larvae that cause malaria [33, 154]. *Scadoxus multiflorus* leaves extract-based ZnONPs exhibited effective ovicidal and larvicidal properties against the fungal agents (*Aspergillus flavus* and *Aspergillus niger*) and insects [14]. The effects of biosynthesized ZnONPs treatment on the morphology and histology of mosquito larvae have been monitored and that revealed significant larvicidal activity [60, 83].

#### ANTICANCER ACTIVITY

In 2020, approximately 10 million deaths were registered in the world due to cancer [153]. Standard cancer treatment options including surgery, chemotherapy, and radiation therapy have harmful side effects [41].

Alternative cancer treatments are requested to overcome these limitations, and the potential candidates are biosynthesized nanomaterials with a targeted drug therapy approaches that reduce side effects [146]. ZnONPs have excellent anticancer properties, and their effects increased while their concentration increased [9, 62, 128].

#### PHOTOVOLTAIC APPLICATION

Nanomaterials are widely used in solar energy production and are expected to reduce the cost and improve the performance of solar devices [59]. ZnO is an inorganic semiconductor of low cost and easy synthesis. Moreover, ZnO has good optoelectronic properties (high conductivity, high electron affinity, and excellent electron mobility), non-toxicity, and high stability. ZnONPs have been used in solar cells, supercapacitors, flexible piezoelectric nanogenerators, ultraviolet photodetectors, and photodiodes. Many organic and hybrid solar cells have been investigated since these remarkable properties were discovered for ZnONPs [105, 168]. A dye-sensitized solar cell (DSSC) is a photovoltaic device based on electrochemical principles that converts visible light into electricity, through sensitive dye absorption [99]. ZnO is an important photoanode semiconductor for DSSC [45, 169].

One-dimensional ZnO nanostructures are used in DSSC due to their high electron transport with a low yield. Furthermore, their incorporation into porous films increased their efficiency [57]. Shashanka *et al.* fabricated a ZnONP-based dye solar cell from *Tilia tomentosa* leaf extract, and their characteristics have been performed and high efficiency was observed [144]. Synthesized DSSCs using dyes extracted from *Ixora* flower, *Pongame* leaf, *Neem* leaf, and *almond* fruit were investigated, and the efficiency of the *almond* extract solar cells was higher than that of the other four solar cells [135]. Optoelectronic studies were performed on ZnO nanoflowers synthesized from watermelon rind agricultural waste that demonstrated a potential use as a photosensitive device like solar cells, LEDs, and photodetectors

[147]. ZnONPs synthesized using the *Terminalia* leaf extract were used as a photoanode in the DSSC fabrication with higher efficiency at pH = 9 [46]. The ZnONPs-based DSSCs using different plant extracts (onion, cabbage, carrot, and tomato) were investigated by measuring the voltage-current density behavior in the presence of artificial sunshine [37]. ZnONPs-based DSSC from methyl orange dye reached an efficiency of 2.3 % [13]. Figure 4 presents an overview of diverse fields of application of ZnONPs.




Fig. 4. Main characterization techniques of ZnONPs.

## CONCLUSION AND FUTURE PERSPECTIVES

This review provides a state-of-the-art overview of synthesis methods, characterization techniques, and potential applications of biosynthesized ZnONPs from different biological sources. It demonstrates that ZnONPs display a range of favorable properties for diverse applications. Green synthesis approaches using a variety of plants, fungi, bacteria, and algae are widely explored and adopted nowadays because of their low cost and environmentally friendly protocols. The active molecules such as phenols, flavonoids, saponins, glycosides, steroids, amino acids, tannins, and alkaloids found in these different species are used as stabilizing and reducing agents.

ZnONPs stand out as one of the most versatile materials, due to their remarkable properties and functionalities, which lead to applications in fundamental research and diverse technological fields. Further research on the green synthesis of

nanoparticles, and in particular on ZnONPs, may focus on the development of industrial-scale applications.

*Acknowledgements.* The authors acknowledge the staff at the Laboratoire de Physique des Matériaux et des Composants à Semi-conducteurs (LPMCS) at the University of Lomé. The authors are grateful for the financial support from the Swedish International Development Agency (SIDA) through the International Science Program (ISP, Uppsala) through a grant to the African Spectral Imaging Network (AFSIN). Prof. Dzagli acknowledge the staff of the Centre d'Excellence Regional pour la Maîtrise de l'Electricité (CERME), at the University of Lomé.

#### REFERENCES

1. ABDELBAKY, A.S., T.A. ABD EL-MAGEED, A.O. BABALGHITH, S. SELIM, A.M.H.A. MOHAMED, Green synthesis and characterization of ZnO nanoparticles using *Pelargonium odoratissimum* (L.) aqueous leaf extract and their antioxidant, antibacterial and anti-inflammatory activities, *Antioxidants*, 2022, **11**(8), 1444 (1–25).
2. ABOMUTI, M.A., E.Y. DANISH, A. FIROZ, N. HASAN, M.A. MALIK, Green synthesis of zinc oxide nanoparticles using *Salvia officinalis* leaf extract and their photocatalytic and antifungal activities, *Biology*, 2021, **10**(11), 1075 (1–26).
3. ABREU, R., T. SEMEDO-LEMSADDEK, E. CUNHA, L. TAVARES, M. OLIVEIRA, Antimicrobial drug resistance in poultry production: Current status and innovative strategies for bacterial control, *Microorganisms*, 2023, **11**(4), 953 (1–35).
4. AGARWAL, H., S. VENKAT KUMAR, S. RAJESHKUMAR, A review on green synthesis of zinc oxide nanoparticles – An eco-friendly approach, *Resource-Efficient Technologies*, 2017, **3**(4), 406–413.
5. AHAMAD KHAN, M., S.A. LONE, M. SHAHID, M.T. ZEYAD, A. SYED, A. EHTRAM, A.M. ELGORBAN, M. VERMA, M. DANISH, Phylogenically synthesized zinc oxide nanoparticles (ZnO-NPs) potentially inhibit the bacterial pathogens: in vitro studies, *Toxics*, 2023, **11**(5), 452 (1–23).
6. AKHTER, S., M.H. MAHMOOD, S. AHMAD, F. MOHAMMAD, Plant-mediated green synthesis of zinc oxide nanoparticles using *Swertia chirayita* leaf extract, characterization and its antibacterial efficacy against some common pathogenic bacteria, *BioNanoScience*, 2018, **8**, 811–817.
7. AKINTELU, S.A., A.S. FOLORUNSO, A review on green synthesis of zinc oxide nanoparticles using plant extracts and its biomedical applications, *BioNanoSci.*, 2020, **10**, 848–863.
8. AKINTELU, S.A., A.S. FOLORUNSO, O.T. ADEMOSUN, Instrumental characterization and antibacterial investigation of silver nanoparticles synthesized from *Garcinia kola* leaf, *J. Drug Deliv. Ther.*, 2019, **9**(6-s), 58–64.
9. AL-AJMI, M.F., E. HUSSAIN, F. AHMED, S. AMIR, M.S. ANWAR; M. SIDDIQUI, A.A. AL-KHEDHAIRY, B.H. KOO, Green synthesis of zinc oxide nanoparticles using *Alstonia macrophylla* leaf extract and their *in vitro* anticancer activity, *Sci. Adv. Mater.*, 2018, **10**(3), 349–355.
10. AL-HRAISAWI, H., N. AL-SAADY, S. JABBAR, *In vitro* analysis: the anticancer activity of zinc oxide nanoparticles from *Cinnamomum verum*, *J. Nanostruct.*, 2023, **13**(1), 146–150.
11. AL JABRI, H., M.H. SALEEM, M. RIZWAN, I. HUSSAIN, K. USMAN, M. ALSAFRAN, Zinc oxide nanoparticles and their biosynthesis: overview, *Life*, 2022, **12**(4), 594 (1–28).
12. ALAMDARI, S., M. SASANI GHAMSARI; C. LEE, W. HAN, H. PARK, M. TAFRESHI, H. AFARIDEH, M. ARA, Preparation and characterization of zinc oxide nanoparticles using leaf extract of *Sambucus ebulus*, *Appl. Sci.*, 2020, **10**(10), 3620 (1–19).
13. AL-BYATI, M.K.A.A., A.M.J. AL-DUHAIHAHAWI, Synthesis and characterization of zinc oxide nanoparticles by electrochemical method for environmentally friendly dye-sensitized solar cell applications (DSSCs), *Biomedicine and Chemical Sciences*, 2023 **2**(1), 53–57.

14. AL-DHABI, N.A., M. VALAN ARASU, Characterization of silver nanomaterials derived from *Marine streptomyces sp. Al-Dhabi-87* and its *in vitro* application against multidrug resistant and extended-spectrum beta-lactamase clinical pathogens, *Nanomater.*, 2018, **8**(5), 279 (1–13).
15. ALI, K., S. DWIVEDI, A. AZAM, Q. SAQUIB, M.S. AL-SAID, A.A. ALKHEDHAIRY, J. MUSARRAT, *Aloe vera* extract functionalized zinc oxide nanoparticles as nanoantibiotics against multi-drug resistant clinical bacterial isolates, *J. Colloid Interface Sci.*, 2016, **472**, 145–156.
16. ALPROL, A.E., A.T. MANSOUR, A. ABDELWAHAB, M. ASHOUR, Advances in green synthesis of metal oxide nanoparticles by marine algae for wastewater treatment by adsorption and photocatalysis techniques, *Catalysts*, 2023, **13**(5), 888 (1–25).
17. ALPROL, A.E., A.T. MANSOUR, H.S. EL-BELAGI, M. ASHOUR, Algal extracts for green synthesis of zinc oxide nanoparticles: promising approach for algae bioremediation, *Materials – (Basel)*, 2023, **16**(7), 2819 (1–23).
18. ÁLVAREZ-CHIMAL, R., V.I. GARCÍA-PÉREZ, M.A. ALVAREZ-PEREZ, J.Á. ARENAS-ALATORRE, Green synthesis of ZnO nanoparticles using a *Dysphania ambrosioides* extract. Structural characterization and antibacterial properties, *Mater. Sci. Eng. C*, 2021, **118**, 111540 (1–13).
19. ALZUBAIDI, A.K., W.J. AL- KAABI, A.A. ALI, S. ALBUKHATY, H. AL- KARAGOLY, G.M. SULAIMAN, M. ASIRI, Y. KHANE, Green synthesis and characterization of silver nanoparticles using *Flaxseed* extract and evaluation of their antibacterial and antioxidant activities, *Appl. Sci.*, 2023, **13**(4), 2182 (1–14).
20. AMINUZZAMAN, M., L.P. YING, W.S. GOH, A. WATANABE, Green synthesis of zinc oxide nanoparticles using aqueous extract of *Garcinia mangostana* fruit pericarp and their photocatalytic activity, *Bull. Mater. Sci.*, 2018, **41**(2), 50 (1–10).
21. ANBUVANNAN, M., M. RAMESH, G. VIRUTHAGIRI, N. SHANMUGAM, N. KANNADASAN, Anisochilus carnosus leaf extract mediated synthesis of zinc oxide nanoparticles for antibacterial and photocatalytic activities, *Mat. Sci. Semicon. Proc.*, 2015, **39**, 621–628.
22. ARCHANA, P., B. JANARTHANAN, S. BHUVANA, P. RAJIV, S. SHARMILA, Concert of zinc oxide nanoparticles synthesized using *Cucumis melo* by green synthesis and the antibacterial activity on pathogenic bacteria, *Inorg. Chem. Commun.*, 2022, **137**, 109255 (1–7).
23. ASIF, N., M. AMIR, T. FATMA, Recent advances in the synthesis, characterization and biomedical applications of zinc oxide nanoparticles, *Bioproc. Biosyst. Eng.*, 2023, **46**, 1377–1398.
24. AYOUB, I., V. KUMAR, R. ABOLHASSANI, R. SEHGAL, V. SHARMA, R. SEHGAL, H. SWART, Y. MISHRA, Advances in ZnO: manipulation of defects for enhancing their technological potentials, *Nanotechnol. Rev.*, 2022, **11**(1), 575–619.
25. AZIZI, S., M.B. AHMAD, F. NAMVAR, R. MOHAMAD, Green biosynthesis and characterization of zinc oxide nanoparticles using brown marine macroalga *Sargassum muticum* aqueous extract, *Mater. Lett.*, 2014, **116**, 275–277.
26. BALA, N., S. SAHA, M. CHAKRABORTY, M. MAITI, S. DAS, R. BASU, P. NANDY, Green synthesis of zinc oxide nanoparticles using *Hibiscus subdariffa* leaf extract: effect of temperature on synthesis, anti-bacterial activity and anti-diabetic activity, *RSC Adv.*, 2015, **5**, 4993–5003.
27. BANDEIRA, M., M. GIOVANELA, M. ROESCH-ELY, D.M. GUESS, J. DA SILVA CRESPO, Green synthesis of zinc oxide nanoparticles: A review of the synthesis methodology and mechanism of formation, *Sustain. Chem. Pharm.*, 2020, **15**, 100223 (1–10).
28. BARANI, D., B. BENHAOUA, S.E. LAOUINI, H. BENTEMAM, N. ALLAG, D. BERRA, A. GUERRAM, Green synthesis of ZnO nanoparticles using *Phoenix dactylifera*. L leaf extract: effect of zinc acetate concentration on the type of product, *Dig. J. Nanomater. Bios.*, 2019, **14**(3), 581–591.
29. BATSMANOVA, L.M., L.M. GONCHAR, N.Y. TARAN, A.A. OKANENKO, Using a colloidal solution of metal nanoparticles as micronutrient fertiliser for cereals, *Proc. Int. Conf.*

- Nanomater.: Appl. Prop.* (NAP2013, Sep 16–21, 2013), 2013, **2**(4), 04NABM14 (1–2), Alushta, The Crimea, Ukraine.
30. BEKKARI, R., L. LAÂNAB, D. BOYER, R. MAHIOU, B. JABER, Influence of the sol gel synthesis parameters on the photoluminescence properties of ZnO nanoparticles, *Mater. Sci. Semicond. Process.*, 2017, **71**, 181–187.
  31. BUSI, S., J. RAJKUMARI, S. PATTNAIK, P. PARASURAMAN, S.H.S. HNAME, Extracellular synthesis of zinc oxide nanoparticles using *Acinetobacter schindleri* SIZ7 and its antimicrobial property against foodborne pathogens, *J. Microbiol. Biotechnol. Food Sci.*, 2016, **5**(5), 407–411.
  32. CHAKRABORTY, P., A. BANERJEE, S. CHANDA, K. RAY, K. ACHARYA, J. SARKAR, Green synthesis of copper/copper oxide nanoparticles and their applications: a review, *Green Chem. Lett. Rev.*, 2022, **15**(1), 187–215.
  33. CHAN, Y.Y., Y.L. PANG, S. LIM, W.C. CHONG, Facile green synthesis of ZnO nanoparticles using natural-based materials: properties, mechanism, surface modification and application, *J. Environ. Chem. Eng.*, 2021, **9**, 105417 (1–27).
  34. CHINNAPAIYAN, M., Y. SELVAM, F. BASSYOUNI, M. RAMU, C. SAKKARAVEERANAN, A. SAMICKANNIAN, G. GOVINDAN, M. PALANISWAMY, U. RAMAMURTHY, M. ABDEL-REHIM, Nanotechnology, green synthesis and biological activity application of zinc oxide nanoparticles incorporated *Argemone mexicana* leaf extract, *Molecules*, 2022, **27**(5), 1545 (1–13).
  35. DANGANA, R.S., R.C. GEORGE, F.K. AGBOOLA, The biosynthesis of zinc oxide nanoparticles using aqueous leaf extracts of *Cnidioscolus aconitifolius* and their biological activities, *Green Chem. Lett. Rev.*, 2023, **16**, 2169591 (1–11).
  36. DANGANA, R.S., R.C. GEORGE, U.O. SHITTU, F.K. AGBOOLA, Facile biosynthesis, characterisation and biotechnological application of ZnO nanoparticles mediated by leaves of *Cnidioscolus aconitifolius*, *Artificial Cells, Nanomedicine, and Biotechnology*, 2023, **51** (1), 309–317.
  37. DEGEFA, A., B. BEKELE, L.T. JULE, B. FIKADU, S. RAMASWAMY, L.P. DWARAMPUDI, N. NAGAPRASAD, K. RAMASWAMY, Green synthesis, characterization of zinc oxide nanoparticles, and examination of properties for dye-sensitive solar cells using various vegetable extracts, *J. Nanomater.*, 2021, **2021**, 3941923 (1–9).
  38. DHANDAPANI, V., A.S. SIDDARTH, S. KAMALASEKARAN, S. MARUTHAMUTHU, G. RAJAGOPAL, Bio-approach: Ureolytic bacteria mediated synthesis of ZnO nanocrystals on cotton fabric and evaluation of their antibacterial properties, *Carbohydr. Polym.*, 2014, **103**, 448–455.
  39. DIALLO, A., B.D. NGOM, E. PARK, M. MAAZA, Green synthesis of ZnO nanoparticles by *Aspalathus linearis*: Structural & optical properties, *J. Alloys Compd.*, 2015, **646**, 425–430.
  40. DIMAPILIS, E.A.S., C.S. HSU, R.M.O. MENDOZA, M.C. LU, Zinc oxide nanoparticles for water disinfection, *Sustain. Environ. Res.*, 2018, **28**, 47–56.
  41. DŁUGOSZ, O., W. MATYJASIK, G. HODACKA, K. SZOSTAK, J. MATYSIK, P. KRAWCZYK, A. PIASEK, J. PULIT-PROCIAK, M. BANACH, Inorganic nanomaterials used in anti-cancer therapies: further developments, *Nanomaterials*, 2023, **13**(6), 1130 (1–30).
  42. DOBRUCKA, R., J. DŁUGASZEWSKA, Biosynthesis and antibacterial activity of ZnO nanoparticles using *Trifolium pratense* flower extract, *Saudi J. Biol. Sci.*, 2016, **23**, 517–523.
  43. ELMER, W.H., J.C. WHITE, The use of metallic oxide nanoparticles to enhance growth of tomatoes and eggplants in disease infested soil or soilless medium, *Environ. Sci. Nano*, 2016, **3**, 1072–1079.
  44. ELUMALAI, K., S. VELMURUGAN, Green synthesis, characterization and antimicrobial activities of zinc oxide nanoparticles from the leaf extract of *Azadirachta indica* (L.), *Appl. Surf. Sci.*, 2015, **345**, 329–336.
  45. ESAKKI, E.S., R. SARATHI, S.M. SUNDAR, L.R. DEVI, Fabrication of dye sensitized solar cells using *Ixora macrothyrsa*, *Materials Today: Proceedings*, 2021, **47**, 2182–2187.
  46. ESAKKI, E.S., SHEEBA, S.M. SUNDAR, Fabrication of dye-sensitised solar cells using four natural sensitizers of ZnO nanoparticle at different pH values, *Int. J. Renew. Energy Technol.*, 2022, **13**, 321–340.

47. EZEALISIJ, K.M., X. SIWE-NOUNDOU, B. MADUELOSI, N. NWACHUKWU, R.W.M. KRAUSE, Green synthesis of zinc oxide nanoparticles using *Solanum torvum* (L) leaf extract and evaluation of the toxicological profile of the ZnO nanoparticles-hydrogel composite in *Wistar albino* rats, *Int. Nano Lett.*, 2019, **9**, 99–107.
48. FAGIER, M.A., Plant-mediated biosynthesis and photocatalysis activities of zinc oxide nanoparticles: a prospect towards dyes mineralization, *J. Nanotechnol.*, 2021, **1**, 6629180 (1–15).
49. FAISAL, S., H. JAN, S. A. SHAH, S. SHAH, A. KHAN, M.T. AKBAR, M. RIZWAN, F. JAN, WAJIDULLAH, N. AKHTAR, A.S. KHATTAK SYED, Green synthesis of zinc oxide (ZnO) nanoparticles using aqueous fruit extracts of *Myristica fragrans*: their characterizations and biological and environmental applications, *ACS Omega*, 2021, **14**(6), 9709–9722.
50. GARTNER, M., H. STROESCU, D. MITREA, M. NICOLESCU, Various applications of ZnO thin films obtained by chemical routes in the last decade, *Molecules*, 2023, **28**(12), 4674 (1–27).
51. GAUR, J., K. VIKRANT, K.H. KIM, S. KUMAR, M. PAL, Photocatalytic degradation of Congo red dye using zinc oxide nanoparticles prepared using *Carica papaya* leaf extract, *Mater. Today Sustain.*, 2023, **22**, 100339 (1–15).
52. GAWADE, V.V., N.L. GAVADE, H.M. SHINDE, S.B. BABAR, A.N. KADAM, K.M. GARADKAR, Green synthesis of ZnO nanoparticles by using *Calotropis procera* leaves for the photodegradation of methyl orange, *J. Mater. Sci.: Mater. Electron.*, 2017, **28**, 14033–14039.
53. GNANASANGEETHA, D., D. SARALATHAMBAVANI, One pot synthesis of zinc oxide nanoparticles via chemical and green method, *Res. J. Mater. Sci.*, 2013, **1**(7), 1–8.
54. GOMATHI, R., H. SUHANA, Green synthesis, characterization and antimicrobial activity of zinc oxide nanoparticles using *Artemisia pallens* plant extract, *Inorg. Nano-Met. Chem.*, 2021, **51**(12), 1–10.
55. HAMEED, H., A. WAHEED, M. SHARIF, M. SALEEM, A. AFREEN, A. KAMAL, W.A. AL-ONAZI, D.A. AL FARRAJ, S. AHMAD, R.M. MAHMOUD, Green synthesis of zinc oxide (ZnO) nanoparticles from green algae and their assessment in various biological applications, *Micromachines*, 2023, **14**(5), 928928 (1–13).
56. HAMRAYEV, H., K. SHAMELI, S. KORPAYEV, Green synthesis of zinc oxide nanoparticles and its biomedical applications: A review, *J. Nanosci. Nanotechnol.*, 2021, **1**(1), 62–74.
57. HSU, Y.F., Y.Y. XI, C.T. YIP, A.B. DJURIŠIĆ, W.K. CHAN, Dye-sensitized solar cells using ZnO tetrapods, *J. Appl. Phys.*, 2008, **103**(8), 083114 (1–4).
58. HUSSEIN, B.Y., A. M. MOHAMMED, Green synthesis of ZnO nanoparticles in grape extract: Their application as anti-cancer and anti-bacterial, *Mater. Today: Proc.*, 2021, **42**, Part 2, A18–A26.
59. HUSSEIN, H.S., The state of the art of nanomaterials and its applications in energy saving, *Bull. Natl. Res. Cent.*, 2023, **47**(7), 1–22.
60. ISHWARYA, R., B. VASEEHARAN, S. KALYANI, B. BANUMATHI, M. GOVINDARAJAN, N.S. MARIMUTHU, S. KADAIKUNNAN, M.N. AL-ANBR, J.M. KHALED, G. BENELLI, Facile green synthesis of zinc oxide nanoparticles using *Ulva lactuca* seaweed extract and evaluation of their photocatalytic, antibiofilm and insecticidal activity, *J. Photochem. Photobiol. B, Biol.*, 2018, **178**, 249–258.
61. ISHWARYA, R., G. TAMILMANI, R. JAYAKUMAR, M.F. ALBESHR, S. MAHBOOB, D. SHAHID, M.N. RIAZ, M. GOVINDARAJAN, B. VASEEHARAN, Synthesis of zinc oxide nanoparticles using *Vigna mungo* seed husk extract: An enhanced antibacterial, anticancer activity and eco-friendly bio-toxicity assessment on algae and zooplankton, *J. Drug. Deliv. Sci. Technol.*, 2023, **79**, 104002 (1–13).
62. ISIK, T., E.H. MOHAMED, N. HORZUM, Green synthesis of zinc oxide nanostructures, In: *Zinc Oxide Based Nanomaterials and Devices*, A.M. NAHHAS ed., *IntechOpen*, 2019, pp. 1–29.
63. ITROUTWAR, P.D., K. GOVINDARAIU, S. TAMILSELVAN, M. KANNAN, K. RAIA, K.S. SUBRAMANIAN, Seaweed-based biogenic ZnO nanoparticles for improving agro-morphological characteristics of rice (*Oryza sativa* L.), *J. Plant Growth Regul.*, 2020, **39**, 717–728.

64. JAFARZADEH, S., M. NOOSHKAM, M. ZARGAR, F. GARAVAND, S. GHOSH, M. HADIDI, M. FOROUGH, Green synthesis of nanomaterials for smart biopolymer packaging: challenges and outlooks, *J. Nanostruct. Chem.*, 2024, **14**, 113–136.
65. JAYACHANDRAN, A., TR. ASWATHY, A.S. NAIR, Green synthesis and characterization of zinc oxide nanoparticles using *Cayratia pedata* leaf extract, *Biochem. Biophys. Rep.*, 2021, **26**, 100995 (1–8).
66. JAYASEELAN, C., A.A. RAHUMAN, A.V. KIRTHI, S. MARIMUTHU, T. SANTHOSHKUMAR, A. BAGAVAN, K. GAURAV, L. KARTHIK, K.V.B. RAO, Novel microbial route to synthesize ZnO nanoparticles using *Aeromonas hydrophila* and their activity against pathogenic bacteria and fungi, *Spectrochim. Acta A Mol. Biomol. Spectrosc.*, 2012, **90**, 78–84.
67. KAHSAY, M. H., Synthesis and characterization of ZnO nanoparticles using aqueous extract of *Becium grandiflorum* for antimicrobial activity and adsorption of methylene blue, *Appl. Water Sci.*, 2021, **11**(45), 1–12.
68. KALPANA, V.N., V. DEVIRAJESWARI, A review on green synthesis, biomedical applications, and toxicity studies of ZnO NPs, *Bioinorg Chem Appl.*, 2018, **2018**, e3569758 (1–12).
69. KAMAL, A., M. SABA, A. KAMAL, M. BATOOL, M. ASIF, A.M. AL-MOHAIMEED, D.A. AL FARRAJ, D. HABIB, S. AHMAD, Bioinspired green synthesis of bimetallic iron and zinc oxide nanoparticles using mushroom extract and use against *Aspergillus niger*. The most devastating fungi of the green world, *Catalysts*, 2023, **13**(2), 400 (1–13).
70. KAVITHA, A., A. DOSS, P.R. PRAVEEN POLE, T.P.K. PUSHPA RANI, R. PRASAD, S. SATHEESH, A mini review on plant-mediated zinc oxide nanoparticles and their antibacterial potency, *Biocatal. Agric. Biotechnol.*, 2023, **48**, 102654 (1–13).
71. KHAN, A.U., N. MALIK, SINGH, N.H. ANSARI, M. REHMAN, A. YADAV, Biosynthesis, and characterization of zinc oxide nanoparticles (ZnONPs) obtained from the extract of waste of strawberry, *Journal of Umm Al-Qura University for Applied Sciences*, 2023, **9**, 268–275.
72. KHAN, J., I. NASEEM, S. BIBI, S. AHMAD, F. ALTAF, M. HAFEEZ, M.M. ALMONEEF, K. AHMAD, Green synthesis of silver nanoparticles (Ag-NPs) using *Debregeasia salicifolia* for biological applications, *Materials*, 2023, **16**(1), 129 (1–13).
73. KHAN, M., P. WARE, N. SHIMPI, Synthesis of ZnO nanoparticles using peels of *Passiflora foetida* and study of its activity as an efficient catalyst for the degradation of hazardous organic dye, *SN Appl. Sci.*, 2021, **3**, 528 (1–17).
74. KHAN, Y., H. SADIA, S.Z. ALI SHAH, M.N. KHAN, A.A. SHAH, N. ULLAH, M.F. ULLAH, H. BIBI, O.T. BAFAKEEH, N.B. KHEDHER, S.M. EL-DIN, B.M. FADHL, M. I. KHAN, Classification, synthetic, and characterization approaches to nanoparticles, and their applications in various fields of nanotechnology: A review, *Catalysts*, 2022, **12**, 1386 (1–27).
75. KHAOULA, H., E.A.M. HAMZA, G. SURESH, M. MAAZA, Green synthesis of cerium oxide nanoparticles using *Portulaca oleracea* extract: Photocatalytic activities, *Inorg. Chem. Commun.*, 2024, **162**, 112243 (1–9).
76. KUMAR, V., R.K. GUNDAMPATI, D. K. SINGH, M.V. JAGANNADHAM, S. SUNDAR, S.H. HASAN, Photoinduced green synthesis of silver nanoparticles with highly effective antibacterial and hydrogen peroxide sensing properties, *J. Photochem. Photobiol. B Biol.*, 2016, **162**, 374–385.
77. KUNDU, D., C. HAZRA, A. CHATTERJEE, A. CHAUDHARI, S. MISHRA, Extracellular biosynthesis of zinc oxide nanoparticles using *Rhodococcus pyridinivorans* NT2: Multifunctional textile finishing, biosafety evaluation and in vitro drug delivery in colon carcinoma, *J. Photochem. Photobiol. B, Biol.*, 2014, **140**, 194–204.
78. LIN, L., H. YANG, X. XU, Effects of water pollution on human health and disease heterogeneity: a review, *Front. Environ. Sci.*, 2022, **10**, 880246 (1–16).
79. LIN, S.T., M. THIRUMAVALAVAN, T.Y. JIANG, J.F. LEE, Synthesis of ZnO/Zn nano photocatalyst using modified polysaccharides for photodegradation of dyes, *Carbohydr. Polym.*, 2014, **105**, 1–9.

80. MA, H., P.L. WILLIAMS, S.A. DIAMOND, Ecotoxicity of manufactured ZnO nanoparticles – A review, *Environ. Pollut.*, 2013, **172**, 76–85.
81. MAHDAVI, M., F. NAMVAR, M.B. AHMAD, R. MOHAMMAD, Green biosynthesis and characterization of magnetic iron oxide (Fe<sub>3</sub>O<sub>4</sub>) nanoparticles using seaweed (*Sargassum muticum*) aqueous extract, *Molecules*, 2013, **18**(5), 5954–5964.
82. MAHMOOD, A.A.H.A., A.A. HASSAN, Green synthesis of ZnO NPs using *Pontederia crassipes* leaf extract: characterization, their adsorption behavior and anti-cancer property, *Biomass Conv. Bioref.*, 2024, **14**(9), 10487–10500.
83. MANDAL, A.K., S. KATUWAL, F. TETTEY, A. GUPTA, S. BHATTARAI, S. JAISI, D.P. BHANDARI, A.K. SHAH, N. BHATTARAI, N. PARAJULI, Current research on zinc oxide nanoparticles: synthesis, characterization, and biomedical applications, *Nanomaterials*, 2022, **12**(17), 3066 (1–31).
84. MANOJKUMAR, U., D. KALIANNAN, V. SRINIVASAN, B. BALASUBRAMANIAN, H. KAMYAB, Z.H. MUSSA, J. PALANIYAPPAN, M. MESBAH, S. CHELLIAPAN, S. PALANINAICKER, Green synthesis of zinc oxide nanoparticles using *Brassica oleracea* var. *botrytis* leaf extract: Photocatalytic, antimicrobial and larvicidal activity, *Chemosphere*, 2023, **323**, 138263 (1–11).
85. MANSOUR, A.T., A.E. ALPROL, M. KHEDAWY, K.M. ABUALNAJA, T.A. SHALABY, G. RAYAN, K.M.A. RAMADAN, M. ASHOUR, Green synthesis of zinc oxide nanoparticles using red seaweed for the elimination of organic toxic dye from an aqueous solution, *Materials*, 2022, **15**(15), 5169 (1–25).
86. MANZOOR, U., F. TUZ ZAHRA, S. RAFIQUE, M.T. MIN, M. MUJAHID, Effect of synthesis temperature, nucleation time, and postsynthesis heat treatment of ZnO nanoparticles and its sensing properties, *J. Nanomater.*, 2015, **2015**, 189058 (1–6).
87. MAŤÁTKOVÁ, O., J. MICHAILIDU, A. MIŠKOVSKÁ, I. KOLOUCHOVÁ, J. MASAK, A. ČEJKOVÁ, Antimicrobial properties and applications of metal nanoparticles biosynthesized by green methods, *Biotechnol. Adv.*, 2022, **58**, 107905 (1–21).
88. MELK, M.M., S.S. EL-HAWARY, F.R. MELEK, D.O. SALEH, O.M. ALI, M.A. EL RAEY, N.M. SELIM, Nano zinc oxide green-synthesized from *Plumbago auriculata* Lam. alcoholic extract, *Plants*, 2021, **10**, 2447 (1–14).
89. MERUVU, H., M. VANGALAPATI, S.C. CHIPPADA, S.R.J. BAMMIDI, Synthesis and characterization of zinc oxide nanoparticles and its antimicrobial activity against *Bacillus subtilis* and *Escherichia coli*, *Rasayan J. Chem.*, 2011, **4**, 217–222.
90. MFON, R.E., N.I. ODIAKA, A. SARUA, Interactive effect of colloidal solution of zinc oxide nanoparticles biosynthesized using *Ocimum gratissimum* and *Vernonia amygdalina* leaf extracts on the growth of *Amaranthus cruentus* seeds, *Afr. J. Biotechnol.*, 2017, **16**(26), 1481–1489.
91. MILLER, S.A., J.P. FERREIRA, J.T. LEJEUNE, Antimicrobial use and resistance in plant agriculture: A one health perspective, *Agriculture*, 2022, **12**(2), 289 (1–27).
92. MINHAS, L.A., A.S. MUMTAZ, M. KALEEM, D.A. FARRAJ, K. KAMAL, M.A.H. KHALID; R. WAQAR, R. MAHMUD, Green synthesis of zinc oxide nanoparticles using *Nostoc sp.* and their multiple biomedical properties, *Catalysts*, 2023, **13**, 549 (1–17).
93. MIRZAEI, H., M. DARROUDI, Zinc oxide nanoparticles: Biological synthesis and biomedical applications, *J. Ceramint.*, 2017, **43**(1) Part B, 907–914.
94. MUTUKWA, D., R. TAZIWA, L.E. KHOTSENG, A review of the green synthesis of ZnO nanoparticles utilising Southern African indigenous medicinal plants, *Nanomaterials*, 2022, **12**, 3456 (1–22).
95. NAGARAJAN, S., K. ARUMUGAM KUPPUSAMY, Extracellular synthesis of zinc oxide nanoparticle using seaweeds of gulf of Mannar, India, *J. Nanobiotechnology*, 2013, **11**(1), 39 (1–11).
96. NAIEL, B., M. FAWZY, M.W.A. HALMY, A.E.D. MAHMOUD, Green synthesis of zinc oxide nanoparticles using *Sea lavender* (*Limonium pruinatum* L. Chaz.) extract: characterization,



- evaluation of anti-skin cancer, antimicrobial and antioxidant potentials, *Sci. Rep.*, 2022, **12**, 20370 (1–12).
97. NARENDHRAN, S., R. SIVARAJ, Biogenic ZnO nanoparticles synthesized using *L. aculeata* leaf extract and their antifungal activity against plant fungal pathogens, *Bull. Mater. Sci.*, 2016, **39**, 1–5.
98. NAVEED UL HAQ, A., A. NADHMAN, I. ULLAH, G. MUSTAFA, M. YASINZAI, I. KHAN, Synthesis approaches of zinc oxide nanoparticles: the dilemma of ecotoxicity, *J. Nanomater.*, 2017, **2017**, 8510342 (1–14).
99. O'REGAN, B., M. GRÄTZEL, Optical electrochemistry. 2. Real-time spectroscopy of conduction band electrons in a metal oxide semiconductor electrode, *J. Phys. Chem.*, 1991, **95**, 10525–10528.
100. OCHIENG, P.E., E. IWUOHA, I. MICHIRA, M. MASIKINI, J. ONDIEK, P. GITHIRA, G.N. KAMAU, Green route synthesis and characterization of ZnO nanoparticles using *Spathodea campanulata*, *Int. J. BioChemPhysics*, 2015, **23**, 53–61.
101. PACHAIAPPAN, R., L.C. PONCE, K. MANAVALAN, F. AWAD, V.F. RAJAN, Nanoparticles as an exotic antibacterial, antifungal, and antiviral agents, In: *Advances in Nanotechnology for Marine Antifouling*, R.K. GUPTA, A.K. NADDA, T.A. NGUYEN, S. SHARMA, M. BILAL eds., Elsevier, 2023, pp. 231–270.
102. PATEL, D., J.S. JANGWAN, H. CHANDRA, D. PATEL, J.S. JANGWAN, H. CHANDRA, Green synthesis of zinc oxide nanoparticles using leaf extract of *Hedera nepalensis* K. Koch and its biological activity, *Medicinal Plants – International Journal of Phytomedicines and Related Industries*, 2018, **10**, 43–51.
103. PATIL, B.N., T.C. TARANATH, *Limonia acidissima* L. leaf mediated synthesis of zinc oxide nanoparticles: A potent tool against *Mycobacterium tuberculosis*, *Int. J. Mycobacteriol.*, 2016, **5**(2), 197–204.
104. PATIL, N., R. BHASKAR, V. VYAVHARE, R. DHADGE, V. KHAIRE, Y. PATIL, Overview on methods of synthesis of nanoparticles, *Int. J. Curr. Pharm. Res.*, 2021, **13** (2), 11–16.
105. PING, R., R. SHUAI, Y. QI, Fabrications and applications of ZnO nanomaterials in flexible functional devices – A review, *Crit. Rev. Anal. Chem.*, 2019, **49**, 336–349.
106. PRAKASH, M., H.P. KAVITHA, S. ABINAYA, J.P. VENNILA, D. LOHITA, Green synthesis of bismuth-based nanoparticles and its applications – A review, *Sustain. Chem. Pharm.*, 2022, **25**, 100547 (1–19).
107. PRASAD, K., A. K. JHA, ZnO nanoparticles: synthesis and adsorption study, *Natural Science*, 2009, **1**(2), 129–135.
108. PRASAD, T.N.V.K.V., P. SUDHAKAR, Y. SREENIVASULU, P. LATHA, V. MUNASWAMY, V. RAJA REDDY, T.S. SREEPRASAD, P.R. SAJANLAL, T. PRADEEP, Effect of nanoscale zinc oxide particles on the germination, growth and yield of peanut, *J. Plant Nutr.*, 2012, **35**, 905–927.
109. PRIYADHARSHINI, R.I., G. PRASANNARAJ, N. GEETHA, P. VENKATACHALAM, Microwave-mediated extracellular synthesis of metallic silver and zinc oxide nanoparticles using macro-algae (*Gracilaria edulis*) extracts and its anticancer activity against human PC3 cell lines, *Appl. Biochem. Biotechnol.*, 2014, **174**, 2777–2790.
110. PURKAIT, P., A. BHATTACHARYYA, S. ROY, S. MAITRA, G.C. DAS, M. GHOSH CHAUDHURI, Green synthesis of ZnO nanoparticle using *Trema orientalis* (L) leaf: an efficient photocatalyst for degradation of zoxamide fungicide in aqueous organic media under UV light irradiation, *Int. J. Environ. Anal. Chem.*, 2023, **103**, 307–325.
111. QU, J., YUAN X., X. WANG, P. SHAO, Zinc accumulation and synthesis of ZnO nanoparticles using *Physalis alkekengi* L., *Environ. Pollut.*, 2011, **159**, 1783–1788.
112. RAFIQUE, M., R. TAHIR, S.S.A. GILLANI, M.B. TAHIR, M. SHAKIL, T. IQBAL, M.O. ABDELLAHI, Plant-mediated green synthesis of zinc oxide nanoparticles from *Syzygium cumini* for seed germination and wastewater purification, *Int. J. Environ. Anal. Chem.*, 2022, **102**, 23–38.

113. RAHA, S., M. AHMARUZZAMAN, ZnO nanostructured materials and their potential applications: progress, challenges and perspectives, *Nanoscale Adv.*, 2022, **4**, 1868–1925.
114. RAJA, A., S. ASHOKKUMAR, R. PAVITHRA MARTHANDAM, J. JAYACHANDIRAN, C. KHATIWADA, K. KAVIYARASU, R. GANAPATHI RAMAN, M. SWAMINATHAN, Eco-friendly preparation of zinc oxide nanoparticles using *Tabernaemontana divaricata* and its photocatalytic and antimicrobial activity, *J. Photochem. Photobiol. B, Biol.*, 2018, **181**, 53–58.
115. RAJAKUMAR, G., M. THIRUVENGADAM, G. MYDHILI, T. GOMATHI, I.M. CHUNG, Green approach for synthesis of zinc oxide nanoparticles from *Andrographis paniculata* leaf extract and evaluation of their antioxidant, anti-diabetic, and anti-inflammatory activities, *Bioprocess. Biosyst. Eng.*, 2018, **41**, 21–30.
116. RAJENDRAN, S.P., K. SENGODAN, Synthesis and characterization of zinc oxide and iron oxide nanoparticles using *Sesbania grandiflora* leaf extract as reducing agent, *J. Nanosci.*, 2017, **2017**, 8348507 (1–7).
117. RAJESHKUMAR, S., S.V. KUMAR, A. RAMAIAH, H. AGARWAL, T. LAKSHMI, S.M. ROOPAN, Biosynthesis of zinc oxide nanoparticles using *Mangifera indica* leaves and evaluation of their antioxidant and cytotoxic properties in lung cancer (A549) cells, *Enzyme and Microbial Technology*, 2018, **117**, 91–95.
118. RAJIV, P., S. RAJESHWARI VENCKATESH, Bio-fabrication of zinc oxide nanoparticles using leaf extract of *Parthenium hysterophorus* L. and its size-dependent antifungal activity against plant fungal pathogens, *Spectrochim. Acta A Mol. Biomol. Spectrosc.*, 2013, **112**, 384–387.
119. RALIYA, R., J.C. TARAFDAR, ZnO nanoparticle biosynthesis and its effect on phosphorous-mobilizing enzyme secretion and gum contents in *Clusterbean (Cyamopsis tetragonoloba* L.), *Agric. Res.*, 2013, **2**, 48–57.
120. RAMESH, M., M. ANBUVANNAN, G. VIRUTHAGIRI, Green synthesis of ZnO nanoparticles using *Solanum nigrum* leaf extract and their antibacterial activity, *Spectrochim. Acta A Mol. Biomol. Spectrosc.*, 2015, **136**, 864–870.
121. RANI, D., R. SINGH, P. KUSH, P. KUMAR, Nanomaterial-based smart coatings for antibacterial, antifungal, and antiviral activities, In: *Advances in Nanotechnology for Marine Antifouling*, R.K. GUPTA, A.K. NADDA, T.A. NGUYEN, S. SHARMA, M. BILAL eds., Elsevier, 2023, pp. 271–302.
122. RANI, N., S. RANIPATEL, S. BHAVNA, M. SAINI, S. RAWAT, K. SAINI, Characterization and investigation of antioxidant and antimicrobial activity of zinc oxide nanoparticles prepared using leaves extract of *Nyctanthes arbor-tristis*, *Inorg. Chem. Commun.*, 2023, **150**, 110516 (1–14).
123. RANI, S., P. KUMAR, P. DAHIYA, A.S. DANG, P. SUNEJA, Biogenic synthesis of zinc nanoparticles, their applications, and toxicity prospects, *Front. Microbiol.*, 2022, **13**, 824427 (1–15).
124. RAO, M.D., P. GAUTAM, Synthesis and characterization of ZnO nanoflowers using *Chlamydomonas reinhardtii*: A green approach, *Environ. Prog. Sustain. Energy*, 2016, **35**, 1020–1026.
125. RIVERA-YAÑEZ, N., C.R. RIVERA-YAÑEZ, G. POZO-MOLINA, C.F. MÉNDEZ-CATALÁ, J. REYES-REALI, M.I. MENDOZA-RAMOS, A.R. MÉNDEZ-CRUZ, O. NIETO-YAÑEZ, Effects of propolis on infectious diseases of medical relevance, *Biology*, 2021, **10**(5), 428 (1–35).
126. SABIR, S., M. ARSHAD, S.K. CHAUDHARI, Zinc Oxide nanoparticles for revolutionizing agriculture: synthesis and applications, *Sci. World J.*, 2014, 925494 (1–8).
127. SAGAR RAUT, D.P., R.T. THORA, Green synthesis of zinc oxide (ZnO) nanoparticles using *Ocimum tenuiflorum* leaves, *Int. J. Sci. Res.*, 2015, **4**, 1225–1228.
128. SAIMA, R., B. SHAZIA, A. RIZWAN, J. SUMBAL, B. MUHAMMAD, A. AYESHA, A. ASRA; U.A. SAIF, In vitro anticancer activity and comparative green synthesis of ZnO/Ag nanoparticles by *Moringa oleifera*, *Mentha piperita*, and *Citrus lemon*, *Ceram. Int.*, 2023, **49**, 5613–5620.
129. SALEM, S.S., A mini review on green nanotechnology and its development in biological effects, *Arch. Microbiol.*, 2023, **205**(4), 128 (1–15).

130. SANGEETHA, G., S. RAJESHWARI, R. VENCKATESH, Green synthesis of zinc oxide nanoparticles by *Aloe barbadensis* Miller leaf extract: Structure and optical properties, *Mater. Res. Bull.*, 2011, **46**(12), 2560–2566.
131. SANTHOSHKUMAR, J., S.V. KUMAR, S. RAJESHKUMAR, Synthesis of zinc oxide nanoparticles using plant leaf extract against urinary tract infection pathogen, *Resource-Efficient Technologies* 2017, **3**, 459–465.
132. SARKHOSH, S., D. KAHRIZI, E. DARVISHI, M. TOURANG, S. HAGHIGHI-MOOD, P. VAHEDI, S. ERCISLI, Effect of zinc oxide nanoparticles (ZnO-NPs) on seed germination characteristics in two *Brassicaceae* family species: *Camelina sativa* and *Brassica napus* L, *J. Nanomater.*, 2022, **2022**, 1892759 (1–15).
133. SATHISHKUMAR, G., C. RAJKUBERAN, K. MANIKANDAN, S. PRABUKUMAR, J. DANIELJOHN, S. SIVARAMAKRISHNAN, Facile biosynthesis of antimicrobial zinc oxide (ZnO) nanoflakes using leaf extract of *Couroupita guianensis* Aubl, *Mater. Lett.*, 2017, **188**, 383–386.
134. SATTAR, R., M.A. RASOOL, R. QADIR, A.B. SIDDIQUE, M.I. IRFAN, I. SABA, M.T. AKHTAR, M.M. REHMAN, M. MUSTAQEEM, Biogenic synthesis of zinc oxide nanoparticles using leaves extract of *Camellia sinensis* for photocatalytic and biological applications, *J. Optoelectron. Biomed. M.*, 2023, **15**(1), 1–9.
135. SELVA ESAKKI, E., G. DEEPA, P. VIVEK, L. RENUGA, N.L. DEVI, SHEABA, S. MEENAKSHI SUNDAR, Investigation on electrochemical analysis of ZnO nanoparticles and its performance for dye-sensitized solar cells using various natural dyes, *J. Indian Chem. Soc.*, 2023, **100**(2), 100889 (1–10).
136. SELVANATHAN, V., M. AMINUZZAMAN, L.X. TAN, Y.F. WIN, E.S. GUAN CHEAH, Synthesis, characterization, and preliminary *in vitro* antibacterial evaluation of ZnO nanoparticles derived from soursop (*Annona muricata* L.) leaf extract as a green reducing agent, *J. Mater. Res. Technol.*, 2022, **20**, 2931–2941.
137. SELVARAJAN, E., V. MOHANASRINIVASAN, Biosynthesis and characterization of ZnO nanoparticles using *Lactobacillus plantarum* VITES07, *Mater. Lett.*, 2013, **112**(1), 180–182.
138. SENAPATI, S., A. SYED, S. MOEZ, A. KUMAR, A. AHMAD, Intracellular synthesis of gold nanoparticles using alga *Tetraselmis kochinensis*, *Mater. Lett.*, 2012, **79**, 116–118.
139. SESIME, K., M.M. DZAGLI, K.B.R. AFOUDJI, Green synthesis and characterization of zinc oxide nanoparticles using extracts of *Artemisia annua* l. grown in Togo, *J. Optoelectron. Biomed. Mater.*, 2021, **13**(4), 193–201.
140. SHAMSUZZAMAN, A. MASHRAI, H. KHANAM, R.N. ALJAWFI, Biological synthesis of ZnO nanoparticles using *C. albicans* and studying their catalytic performance in the synthesis of steroidal pyrazolines, *Arab. J. Chem.*, 2017, **10**(2), S1530–S1536.
141. SHANMUGAM, R., T. MUNUSAMY, S. JAYAKODI, K.A. AL-GHANIM, M. NICOLETTI, N. SACHIVKINA, M. GOVINDARAJAN, Probiotic-bacteria (*Lactobacillus fermentum*) – wrapped zinc oxide nanoparticles: biosynthesis, characterization, and antibacterial activity, *Fermentation*, 2023, **9**(5), 413 (1–14).
142. SHANMUGASUNDARAM, T., R. BALAGURUNATHAN, Artificial cells, bio-medically active zinc oxide nanoparticles synthesized by using extremophilic actinobacterium, *Streptomyces sp.* (MA30) and its characterization, *Artif. Cells Nanomed. Biotechnol.*, 2017, **45**(8), 1521–1529.
143. SHARMA, D., S. KANCHI, K. BISETTY, Biogenic synthesis of nanoparticles: A review, *Arab. J. Chem.*, 2019, **12**, 3576–3600.
144. SHASHANKA, R., H. ESGIN, V.M. YILMAZ, Y. CAGLARN, Fabrication and characterization of green synthesized ZnO nanoparticle-based dye-sensitized solar cells, *J. Sci-Adv. Mater. Dev.*, 2020, **5**, 185–191.
145. SHEKHAWA, M.S., C.P. RAVINDRAN, M. MANOKARI, A biomimetic approach towards synthesis of zinc oxide nanoparticles using *Hybanthus enneaspermus* (L.) F. Muell., *Trop. Plant Res.*, 2014, **1**(2), 55–59.

146. SINGH, C., I. NASEEM, S. BIBI, S. AHMAD, F. ALTAF, M. HAFEEZ, M. ALMONEEF, K. AHMAD, Green synthesis of silver nanoparticles by root extract of *Premna integrifolia* L. and evaluation of its cytotoxic and antibacterial activity, *Mater. Chem. Phys.*, 2023, **297**, 127413 (1–14).
147. SINGH, S., M. JOSHI PANTHARI, B. MALHOTRA, A.C. KHARKWAL, H. KHARKWAL, Citrulline rich structurally stable zinc oxide nanostructures for superior photo catalytic and optoelectronic applications: A green synthesis approach, *Nano-Structures & Nano-Objects*, 2017, **11**, 1–6.
148. SINGHAL, U., R. PENDURTHI, M. KHANUJA, *Prunus*: A natural source for synthesis of zinc oxide nanoparticles towards photocatalytic and antibacterial applications, *Materials Today: Proceedings*, 2020, **28**, 261–265.
149. SMAOUI, S., I. CHERIF, H. BEN HLIMA, M.U. KHAN, M. REBEZOV, M. THIRUVENGADAM, T. SARKAR, M.A. SHARIATI, J.M. LORENZO, Zinc oxide nanoparticles in meat packaging: A systematic review of recent literature, *Food Packag. Shelf Life*, 2023, **36**, 101045 (1–20).
150. SPORTELLI, M.C., C. GAUDIUSO, A. VOLPE, M. IZZI, R.A. PICCA, A. ANCONA, N. CIOFFI, Biogenic synthesis of ZnO nanoparticles and their application as bioactive agents: A critical overview, *Reactions*, 2022, **3**(3), 423–441.
151. STAN, M., A. POPA, D. TOLOMAN, T.D. SILIPAS, D.C. VODNAR, Antibacterial and antioxidant activities of ZnO nanoparticles synthesized using extracts of *Allium sativum*, *Rosmarinus officinalis* and *Ocimum basilicum*, *Acta Metall. Sin.*, 2016, **29**, 228–236.
152. SUNDRARAJAN, M., S. AMBIKA, K. BHARATHI, Plant-extract mediated synthesis of ZnO nanoparticles using *Pongamia pinnata* and their activity against pathogenic bacteria, *Adv. Powder Technol.*, 2015, **26**, 1294–1299.
153. SUNG, H., J. FERLAY, R.L. SIEGEL, M. LAVERSANNE, I. SOERJOMATARAM, I. SOERJOMATARAM, A. JEMAL, F. BRAY, Global cancer statistics 2020: GLOBOCAN estimates of incidence and mortality worldwide for 36 cancers in 185 countries, *CA Cancer J. Clin.*, 2021, **71**, 209–249.
154. SUPRAJA, N., T.N.V.K.V. PRASAD, T.G. KRISHNA, E. DAVID, Synthesis, characterization, and evaluation of the antimicrobial efficacy of *Boswellia ovalifoliolata* stem bark-extract-mediated zinc oxide nanoparticles, *Appl. Nanosci.*, 2016, **6**, 581–590.
155. SURESH, D., P.C. NETHRAVATHI UDAYABHANU; V. RAJANAIIKA, H. NAGABHUSHANA, S.C. SHARMA, Green synthesis of multifunctional zinc oxide (ZnO) nanoparticles using *Cassia fistula* plant extract and their photodegradative, antioxidant and antibacterial activities, *Mater. Sci. Semicond. Process.*, 2015, **31**, 446–454.
156. TAMBOLI, Q.Y., S.M. PATANGE, Y.K. MOHANTA, R. SHARMA, K.R. ZAKDE, Green synthesis of cobalt ferrite nanoparticles: An emerging material for environmental and biomedical applications, *J. Nanomater.*, 2023, **2023**(8–9) 1–15.
157. THEMA, F.T., E. MANIKANDAN, M.S. DHLAMINI, M. MAAZA, Green synthesis of ZnO nanoparticles via *Agathosma betulina* natural extract, *Mater. Lett.*, 2015, **161**, 124–127.
158. VANATHI, P., P. RAJIV, S. NARENDHRAN, S. RAJESHWARI, P.K.S.M. RAHMAN, R. VENCKATESH, Biosynthesis and characterization of phyto mediated zinc oxide nanoparticles: A green chemistry approach, *Mater. Lett.*, 2014, **134**, 13–15.
159. VANLALVENI, C., S. LALLIANRAWNA, A. BISWAS, M. SELVARAJ, B. CHANGMAI, S. LALTHAZUALA ROKHUM, Green synthesis of silver nanoparticles using plant extracts and their antimicrobial activities: A review of recent literature, *RSC Advances*, 2021, **11**(5), 2804–2837.
160. VERA, J., W. HERRERA, E. HERMOSILLA, M. DÍAZ, J. PARADA, A.B. SEABRA, G. TORTELLA, H. PESENTI, G. CIUDAD, O. RUBILAR, Antioxidant activity as an indicator of the efficiency of plant extract-mediated synthesis of zinc oxide nanoparticles, *Antioxidants*, 2023, **12**, 784 (1–19).
161. VERMA, V., M. AL-DOSSARI, J. SINGH, M. RAWAT, M.G.M. KORDY, M. SHABAN, A review on green synthesis of TiO<sub>2</sub> NPs: Photocatalysis and antimicrobial applications, *Polymers*, 2022, **14**(7), 1444 (1–19).

162. VIDY, A.C., S. HIREMATH, M.N. CHANDRAPRABHA, M.L. ANTONYRAJ, I.V. GOPAL, A. JAIN, K. BANSAL, Green synthesis of ZnO nanoparticles by *Calotropis gigantea*, *Int. J. Curr. Eng. Technol.*, 2013, **1**, 118–120.
163. VIJAYAKUMAR, S., B. VASEEHARAN, B. MALAIKOZHUNDAN, M. SHOBIYA, *Laurus nobilis* leaf extract mediated green synthesis of ZnO nanoparticles: Characterization and biomedical applications, *Biomed. Pharmacother.*, 2016, **84**, 1213–1222.
164. VIJAYAKUMAR, S., C. KRISHNAKUMAR, P. ARULMOZHI, S. MAHADEVAN, N. PARAMESWARI, Biosynthesis, characterization and antimicrobial activities of zinc oxide nanoparticles from leaf extract of *Glycosmis pentaphylla* (Retz.) DC, *Microb. Pathog.*, 2018, **116**, 44–48.
165. VIJAYAKUMAR, S., G. VINOJ, B. MALAIKOZHUNDAN, S. SHANTHI, B. VASEEHARAN, *Plectranthus amboinicus* leaf extract mediated synthesis of zinc oxide nanoparticles and its control of methicillin resistant *Staphylococcus aureus* biofilm and blood sucking mosquito larvae, *Spectrochim. Acta A Mol. Biomol. Spectrosc.*, 2015, **137**, 886–891.
166. VIJAYAKUMAR, S., S. MAHADEVAN, P. ARULMOZHI, S. SRIRAM, P. K. PRASEETHA, Green synthesis of zinc oxide nanoparticles using *Atalantia monophylla* leaf extracts: Characterization and antimicrobial analysis, *Mater. Sci. Semicond. Process.*, 2018, **82**, 39–45.
167. VIJAYARAM, S., H. RAZAFINDRALAMBO, Y.Z. SUN, S. VASANTHARAJ, H. GHAFARIFARSANI, S.H. HOSEINIFAR; M. RAEESZADEH, S. NAGARAJAN, K.A. KUPPUSAMY, Applications of green synthesized metal nanoparticles – a Review, *Biol. Trace Elem. Res.*, 2024, **202**, 360–386.
168. WIBOWO, A., M.A. MARSUDI, M. I. AMAL, M.B. ANANDA, R. STEPHANIE, H. ARDY, L. J. DIGUNA, ZnO nanostructured materials for emerging solar cell applications, *RSC Adv.*, 2020, **10**, 42838–42859.
169. WONGCHAREE, K., V. MEEYOO, S. CHAVADEJ, Dye-sensitized solar cell using natural dyes extracted from *Rosella* and *Blue pea* flowers, *Sol. Energy Mater Sol. Cells*, 2007, **91**, 566–571.
170. WU, C., T. ZHANG, B. JI, Y. CHOUL, X. DU, Green synthesis of zinc oxide nanoparticles using *Aloe vera* leaf extract and evaluation of the antimicrobial and antioxidant properties of the ZnO/regenerated cellulose film, *Cellulose*, 2024, **31**, 4849–4864.
171. YEDURKAR, S., C. MAURYA, P. MAHANWAR, Biosynthesis of zinc oxide nanoparticles using *Ixora coccinea* leaf extract - A green approach, *Open J. Synth. Theory Appl.*, 2016, **5**(1), 1–14.
172. ZEGHOUD, S., H. HEMMAMI, B. BEN SEGHIR, I. BEN AMOR, I. KOUADRI, A review on biogenic green synthesis of ZnO nanoparticles by plant biomass and their applications, *Mater. Today Commun.*, 2022, **33**, 104747 (1–10).

